



Wear Components

RAILKO RG15 Technical Data Sheet Product Description RG15 has been specially formulated and manufactured for friction damper applications. RAILKO RG15 friction damper bushes are used to provide optional suspension dampening to the system. RAILKO RG15 offers complete protection against ovalisation to the bogie housing and wear onto the damper plunger which was a common customer problem. **Product Advantages** Protection against housing ovalisation (wear) Excellent impact and vibration absorption Significantly lower noise than steel Low water swell High temperature resistance Outstanding strength capabilities Storage To be stored in a dry location Take care not to exceed safe working loads and heights for storage shelves and racks



Physical Properties

Property	Units	RG15
Density	g/cm³	1.31
Flexural Strength	MPa	100
Flexural Modulus	GPa	4.8
Compressive Strength	MPa	240
Tensile Strength	MPa	60
Charpy Impact Notched	kJ/m²	32
Shear Strength	MPa	80
Compressive Yield @ 68.9 Mpa	%	2.2
Brinell Hardness	kgf/mm²	32
Swell in Water (24 hours)	%	
_20 °C		0.4
80 °C		0.6
Coefficient of Thermal Expansion	x 10-6/°C	
Parallel		30
Perpendicular		52
Coefficient of Friction (Unlubricated)		0.28-0.42
Maximum Operating Temperature	°C	
Continuous		200
Intermittent		220
Normal Working Pressure	MPa	60





RAILKO RG15

Tenmat Ltd Ashburton Rd West, Manchester M17 1TD United Kingdom

+44 161 872 2181 info@tenmat.com

tenmat.com



Advanced materials. tenmat.com

Tenmat warrants the materials it produces will conform to Tenmat specifications and approved drawings where applicable. It is entirely the customer's responsibility to make the final product choice and satisfy themselves of the suitability of the product for the intended application, carrying out testing where required. For construction projects, all products which the customer is intending to use on a particular project must be approved in writing by the customer's building designer, system designer or design control professional, to ensure compliance with the latest regulations.

The information contained in Tenmat data sheets is presented in good faith. The values are "typical only" and are based on test results generally in accordance with BS2782, ASTM, a variety of other main test bodies along with Tenmat internal test methods. These values should not be relied upon for specification purposes or the primary selection of materials. As the data sheet values are typical only, Tenmat does not warrant the conformity of its materials to these properties or the suitability of its materials for any particular purpose. It is the responsibility of the customer to do the necessary testing and satisfy themselves the product is suitable for the intended application.